



CUT STONE
AGED PARCHMENT
 CUT STONE

GEOLOGY

limestone - quarried in USA

COLOR RANGE

buffs, tans, mocha, yellows, and gray

CONSISTENCY BLOCK/SLAB

somewhat consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 119
 = approx 119 pounds per cubic foot

ASTM TESTING DATA

AGED PARCHMENT C97

water absorption—6.53%

specific gravity—1.875 to 1.946

density—119 lbs/ft³

AGED PARCHMENT C170

dry perpendicular—2,320 psi

wet perpendicular—1,650 psi

dry parallel—2,770 psi

wet parallel—1,770 psi

AGED PARCHMENT C1353

abrasion—2.2

AGED PARCHMENT ANSI A326.3

friction—0.82

AGED PARCHMENT C880

flexural strength -wet—550 psi

flexural strength -dry—700 psi

PANEL INSTALLATION SHOWN

Mortar: Western W-11

Joint Type: Raked

Size - 11 5/8" x 23 5/8" sanded finish



www.buechelstone.com

ARCHITECT/DESIGNER INFO

BIM DETAILS - SCAN
Revit, Hatch Patterns,
Seamless Textures,
3-Part Specs, DWGS,
SDS, Warranty



CUT STONE
AGED PARCHMENT
CUT STONE


BRUSHED



BUSHHAMMERED



SANDBLASTED



VELOUR



SANDED

