



CUT STONE
INDIANA SILVERBUFF
CUT STONE

GEOLOGY

limestone - quarried in USA

COLOR RANGE

light buff to light gray

CONSISTENCY BLOCK/SLAB

consistent

WEIGHT CALCULATED IN INCHES

l x w x h / 1728 (inches cubed) x 155
 = approx 155 pounds per cubic foot

ASTM TESTING DATA

INDIANA C97

water absorption—4.84%
 specific gravity—2.27 to 2.28

INDIANA C99

modulus of rupture
 wet perpendicular—653 psi
 wet parallel—727 psi
 dry perpendicular—843 psi
 dry parallel—784 psi

INDIANA C170

compressive strength
 wet perpendicular—5,735 psi
 wet parallel—4,693 psi
 dry perpendicular—6,581 psi
 dry parallel—5,845 psi

INDIANA C880

flexural strength
 wet perpendicular—544 psi
 wet parallel—556 psi
 dry perpendicular—716 psi
 dry parallel—706 psi

PANEL INSTALLATION SHOWN

Mortar: Western W-11

Joint Type: raked

Size - 11 5/8" x 23 5/8" sanded finish



www.buechelstone.com

ARCHITECT/DESIGNER INFO

BIM DETAILS - SCAN
Revit, Hatch Patterns,
Seamless Textures,
3-Part Specs, DWGS,
SDS, Warranty



CUT STONE
INDIANA SILVERBUFF
CUT STONE

BRUSHED



BUSHHAMMERED



SANDBLASTED



VELOUR



SANDED

