



**CUT STONE**  
*RUSTIC BUFF*  
*CUT STONE*

**GEOLOGY**

limestone - quarried in USA

**COLOR RANGE**

light to medium buff with gray

**CONSISTENCY BLOCK/SLAB**

somewhat consistent

**WEIGHT CALCULATED IN INCHES**

$l \times w \times h / 1728$  (inches cubed)  $\times 155 =$   
 approx 155 pounds per cubic foot

**ASTM TESTING DATA**

**RUSTIC BUFF C97**

water absorption—4.84%

**RUSTIC BUFF C97**

specific gravity—2.27 to 2.28

**RUSTIC BUFF C99**

modulus of rupture

wet perpendicular—653 psi

wet parallel—727 psi

dry perpendicular—843 psi

dry parallel—784 psi

**RUSTIC BUFF C170**

compressive strength

wet perpendicular—5,735 psi

wet parallel—4,693 psi

dry perpendicular—6,581 psi

dry parallel—5,845 psi

**RUSTIC BUFF C880**

flexural strength

wet perpendicular—544 psi

wet parallel—556 psi

dry perpendicular—716 psi

dry parallel—706 psi

**PANEL INSTALLATION SHOWN**

Mortar: Laticrete MVIS

Joint Type: drystack

Size: 4" & 8", l: 24" - sandblasted finish



www.buechelstone.com

**ARCHITECT/DESIGNER INFO**

BIM DETAILS - SCAN  
Revit, Hatch Patterns,  
Seamless Textures,  
3-Part Specs, DWGS,  
SDS, Warranty



CUT STONE  
*RUSTIC BUFF*  
CUTSTONE

BRUSHED



BUSHHAMMERED



SANDBLASTED



VELOUR



SANDED

