



OUTCROPPING STEPS

*CHILTON OUTCROPPING
STEPS*



PART NUMBERS
1OUTBUE01006TN

ASTM TESTING DATA

CHILTON C97
water absorption—0.08%
density—177.4 pcf
CHILTON C99
modulus of rupture—1,220 psi
CHILTON C170
compressive strength
w/rift—50,560 psi
compressive strength
across rift—38,090 psi
CHILTON C880
flexural strength—3,070 psi

GEOLOGY

dolomitic limestone

BASIC USE

for steps

COLOR RANGE

top or bottom is purple, lavender, mauve, gray, buff, blue, and brown; face is gray to charcoal with occasional mauves

CONSISTENCY PER PALLET

somewhat consistent

WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$ (inches cubed) $\times 170$
= approx 170 pounds per cubic foot

PALLET

4,000 pounds or as product fits

COVERAGES

calculated as specified per project

DIMENSIONS

l: 18" to 60"
h: 5" to 8"
w: 18" to 60"
note: lengths and widths are irregular shapes 18 inches to 60 inches in diameter

TYPICAL PIECE

ends irregular; natural cleft top and bottom; natural split sides; stone is somewhat square but may be irregular

