



# STEPS

FOND DU LAC SNAPPED STEPS



### PART NUMBERS

18"x36": 1STEBUE02001EA  
24"x36": 1STEBUE02006EA  
18"x48": 1STEBUE02002EA  
24"x48": 1STEBUE02004EA

### ASTM TESTING DATA

FOND DU LAC C97  
water absorption—0.36%  
density—174.2 pcf  
FOND DU LAC C99  
modulus of rupture—1,470 psi  
FOND DU LAC C170  
compressive strength  
w/rift—29,040 psi  
compressive strength  
across rift—34,240 psi  
FOND DU LAC C880  
flexural strength—1,740 psi

### GEOLOGY

dolomitic limestone

### BASIC USE

for steps

### COLOR RANGE

gray, light gray to white, buff

### CONSISTENCY PER PALLET

somewhat consistent

### WEIGHT CALCULATED IN INCHES

$l \times w \times h / 1728$  (inches cubed)  $\times 170$   
= approx 170 pounds per cubic foot

### STEPS PER PALLET

18" x 36" = 8 steps per pallet

24" x 36" = 5 steps per pallet

18" x 48" = 6 steps per pallet

24" x 48" = 5 steps per pallet

### COVERAGES

calculated as specified per project

### 18"x36" SNAPPED STEPS

#### DIMENSIONS

l: 35" to 37"

h: 5" to 8"

w: 17" to 19"

### 24"x36" SNAPPED STEPS

#### DIMENSIONS

l: 35" to 37"

h: 5" to 8"

w: 23" to 25"

### 18"x48" SNAPPED STEPS

#### DIMENSIONS

l: 47" to 49"

h: 5" to 8"

w: 17" to 19"

### 24"x48" SNAPPED STEPS

#### DIMENSIONS

l: 47" to 49"

h: 5" to 8"

w: 23" to 25"

### TYPICAL PIECE

ends square; natural cleft top and bottom; split sides, face and back; stone is rectangular; custom sizing by request